

## SHAPE-SELECTIVE SORBENTS BASED ON CLAY MINERALS: A REVIEW<sup>1</sup>

R. M. BARRER

Chemistry Department, Imperial College, London SW7 2AZ, United Kingdom

**Abstract**—A review is presented of work carried out over the last 40 years on non-porous sorbents and on microporous shape-selective sorbents derived from palygorskite, smectite, and vermiculite. Among such materials four kinds of behavior were observed. In some systems uptake was restricted to external surfaces; in others, intercalation also occurred but only above threshold pressures. If the interlayer region was completely filled by long-chain organic cations, imbibition was possible, but in amounts which were very strongly dependent upon the cohesive energy density of the sorbate. Finally, in certain permanently expanded derivatives of layer silicates intercalation proceeded without any threshold pressure, just as in zeolites.

In this latter group, micropores existed which sometimes resulted in shape-selective sorption and molecule sieving. The micropores in clay minerals were modified by varying the size and shape of the interlayer cations, their charge, and the charge density of the siliceous layers. The interplay of these factors was investigated and the micropore sorbents were shown to be highly effective in the separation of mixtures.

**Key Words**—Adsorption, Imbibition, Intercalation, Palygorskite, Porosity, Shape-selective, Smectite, Vermiculite.

### INTRODUCTION

Over the course of the last 40 years, clay minerals have been studied extensively by the author and co-workers in the Departments of Chemistry, first in the University of Aberdeen and then in the Imperial College in London. The work has consisted of two programs: one on the synthesis and hydrothermal reactions of clay minerals and one on the behavior of clay minerals and their derivatives as sorbents. For reasons of space, this account will deal only with certain parts of the work on sorbents.

### ASPECTS OF SORPTION BY CLAY MINERALS

The parent clay materials, their cation-exchange capacities, external surface areas, and the cationic forms studied are given in Table 1. Four kinds of behavior have been observed:

1. Outgassed smectites containing only small inorganic interlayer cations did not intercalate non-polar molecules, nor did these molecules penetrate the intracrystalline channels present in palygorskite and sepiolite (Barrer and MacLeod, 1954; Barrer and Mackenzie, 1954; Barrer *et al.*, 1954; Barrer and Reay 1957). Sorption isotherms for the external surfaces were of the sigmoid type-2 form (Brunauer, 1944), as illustrated for the attapulgite variety of palygorskite in Figure 1. Hysteresis loops were ob-

served between sorption and desorption branches, which in smectites closed at relative pressures in the range 0.27 to 0.47, according to the sorbate and the temperature.

2. In confirmation of work done elsewhere, outgassed smectites containing only small inorganic interlayer cations intercalated polar molecules. Intercalation occurred only after a threshold pressure was reached, the theoretical basis for which was recently given by Barrer (1984). Isotherms showed one or more steps, and here hysteresis between sorption and desorption branches characteristically persisted to very low relative pressures (Barrer and MacLeod, 1954). These features are illustrated for pyridine and water in Figure 2.
3. Dimethyldioctadecylammonium-montmorillonite (Bentone 34) behaved differently from materials in either of the above categories. Here, the interlayer cations swelled the clay and filled all the interlayer space. The long chains were closely packed and were steeply oriented to the surface. This organoclay imbibed certain molecules with further swelling to give isotherms which in shape resembled type 3 isotherms, like those of benzene in rubber, as seen in Figure 3 (Barrer and Kelsey, 1961b). The extent of imbibition appeared to be controlled by the cohesive energy density (C.E.D.) of the sorbate, as shown by the correlation in Table 2. Maximum uptake should occur if the C.E.D. of the sorbate and of the organic interlayer region, modified by the siliceous layers, most closely matched. That imbibition can be very selective is seen from the relative uptakes of paraffins, aromatics, and heterocycles. The extraction of aromatics and heterocycles from petro-

<sup>1</sup> This paper is based on the Pioneer in Clay Science Lecture delivered at the 25th annual meeting of The Clay Minerals Society in Grand Rapids, Michigan, September 1988.




Figure 1. Type-2 sorption isotherms of (a) n-heptane and (b) iso-octane on attapulgite variety of palygorskite outgassed at 70°C;  $\circ$ ,  $\triangle$ ,  $\square$ , sorption at 50°C;  $\bullet$ , desorption at 50°C (Barrer and Mackenzie, 1954).

leum using Bentone 34 or analogous organosmectites merits further attention.

- If layer silicates were exchanged with ions large enough to hold the layers permanently apart without filling all the interlayer space, a notable range of shape-selective microporous sorbents was obtained, to which the rest of this account will be devoted. Microporosity was first demonstrated in 1955 with  $\text{Me}_4\text{N}^+$  and  $\text{Et}_4\text{N}^+$  as the interlayer cat-




Figure 2. Isotherms at 50°C of pyridine (left) and water (right) on Na-rich montmorillonite, showing steps and hysteresis.  $\circ$ , sorption;  $\times$ , desorption (Barrer and MacLeod, 1954).

ions (Barrer and MacLeod, 1955). The reasoning is seen in Figure 4 (Barrer, 1986). It is  $d_1$  and  $d_3$ , each of molecular dimensions, which control access to the interlayer regions of the crystal. In the  $\text{Me}_4\text{N}$ - and  $\text{Et}_4\text{N}$ -montmorillonites,  $d_1$  was, respectively, 4.1 and 4.5(5) Å. The expanded crystals freely intercalated many permanent gases and non-polar molecules, that were not intercalated in the parent montmorillonite. As a result, the sorption capacity was greatly enhanced and, as with zeolites, intracrystalline sorption required no threshold pressures.

#### INTERLAYER POROSITIES OF SMECTITE MOLECULAR SIEVES

Total micropore volumes were evaluated in some of the sorbate-free outgassed smectites. The total interlamellar area was evaluated for the average number of sheets in the parent crystals. From this, the area occupied by the interlamellar cations was subtracted (with allowance for the fraction of these on external basal surfaces). To obtain the porosity, the net interlamellar area was then multiplied by the free distance between sheets,  $d_1$ . The results, in  $\text{cm}^3/\text{g}$ , are given in Table 3.

Table 1. Clay minerals and exchange forms studied.

Mineral	External area ( $\text{m}^2/\text{g}$ )	CEC <sup>1</sup> (meq/100 g)	Cationic forms <sup>2</sup>
FH150 <sup>3</sup>	8	150	Na, Cs, $\text{MeNH}_3$ , $\text{Me}_4\text{N}$ , $\text{NH}_3(\text{CH}_2)_2\text{NH}_3$ , $\text{Co(III)(en)}_3$
FH90 <sup>3</sup>	11	90	
Montmorillonite (as Bentone 34)	14.8	—	$\text{Me}_2\text{N}(\text{C}_{18}\text{H}_{37})_2$
Montmorillonite A (Na-rich)	21.7	91	Na, $\text{NH}_4$ , Cs, $\text{MeNH}_3$ , $\text{Me}_2\text{NH}_2$ , $\text{Me}_3\text{NH}$ , $\text{Me}_4\text{N}$ , $\text{Et}_4\text{N}$ , $n\text{-C}_n\text{H}_{2n+1}\text{NH}_3$ ( $n = 2, 3, 4, 5, 12$ ), $\text{NH}_3\text{NH}_3$ , $\text{NH}_3(\text{CH}_2)_n\text{NH}_3$ ( $n = 2$ to 10, and 12)
Hectorite (as Ben-a-Gel)	81.4	90	$\text{NH}_4$ , $\text{NH}_3(\text{CH}_2)_n\text{NH}_3$ ( $n = 2, 3, 4, 5, 9, 12$ )
Montmorillonite B (Ca-rich)	85.4	102	Ca, $\text{MeNH}_3$ , $\text{Me}_4\text{N}$
Palygorskite, variety attapulgite	195 (max.)	—	natural

<sup>1</sup> Cation-exchange capacity.

<sup>2</sup> Me = methyl; Et = ethyl; en = ethylenediamine.

<sup>3</sup> FH150 and FH90 = fluorhectorites having CECs of 150 and 90 meq/100 g, respectively (see Barrer and Jones, 1970).




Figure 3. Isotherms at 60°C of toluene and ethylbenzene in extracted, outgassed Bentone 34, showing the type-3 isotherm contours. O, sorption; ●, desorption (Barrer and Kelsey, 1961b).

The micropore volumes are considerable, although somewhat less than those in most zeolites.

The free distance,  $d_1$ , between sheets sometimes expanded further if guest molecules were intercalated. An evaluation of microporosity was therefore also made, this time for fluorhectorite-90 and -150 filled with guest molecules. The BET value of the saturation uptake,  $v_m$ , was corrected for adsorption on the external surface, and it was next found what volume of liquid sorbate the corrected  $v_m$  would represent. This was taken as the pore volume, the results being given in Table 4 (Barrer and Jones, 1971).

The micropore volumes were readily accessible for molecules of appropriate shape and size, and the resultant selectivities made these microporous smectites of very considerable interest. Various large molecules, such as *n*-octane (Figure 5), were rapidly intercalated

Table 2. Cohesive energy densities (C.E.D.) and total uptake at relative pressure 0.2 in Bentone 34 (Barrer and Kelsey, 1961b).

Sorbate	(C.E.D.) <sup>a</sup> (cal/cm <sup>3</sup> ) <sup>b</sup>	Temp. (°C)	Uptake (mmole/g)	d(001) <sup>1</sup> (Å)
iso-C <sub>4</sub> H <sub>10</sub>	6.25	-30	0.06 <sub>2</sub>	—
n-C <sub>4</sub> H <sub>10</sub>	6.7	-30	0.07 <sub>7</sub>	—
iso-C <sub>8</sub> H <sub>18</sub>	6.85	45	0.11	23.2
n-C <sub>7</sub> H <sub>16</sub>	7.45	45	0.11	23.2
cyclo-C <sub>6</sub> H <sub>12</sub>	8.20	45	0.16	23.2
ethylbenzene	8.8	60	0.52	—
toluene	8.90	45	0.65	27.2
benzene	9.15	45	0.81	27.2
dioxane	10.0	60	0.92	—
pyridine	10.7	60	1.79	—
nitromethane	12.6	45	1.38	—

<sup>1</sup> d(001) of the parent material extracted with alcohol was ~23.2 Å.




Figure 4. Representation of an unexpanded and a permanently expanded layer silicate, showing the important free distances  $d_1$  and  $d_3$  (Barrer, 1986).

in ethylenediammonium fluorhectorites-90 and -150 (Barrer and Jones, 1971). To minimize external adsorption, the external areas should be as small as possible. These areas for the fluorhectorite samples were only 11 and 8 m<sup>2</sup>/g of parent material (Table 1).

### MODIFYING THE MICROPORES

Ways in which the micropores were modified involved changing  $d_1$  and  $d_3$  of Figure 4 and were explored by: (1) varying the size and shape of the ionic interlayer props; (2) increasing the charge and therefore decreasing the number of the interlayer cations; and (3) altering the composition of the siliceous layers and therefore their anionic charge.

Table 3. Calculated interlayer free areas and porosities of some organomontmorillonites and organohectorites (Barrer and Millington, 1967).

Cation	g.u.c. wt. <sup>1</sup>	Ion co-area (Å <sup>2</sup> )	$d_1^2$ (Å)	Free area (m <sup>2</sup> /g)	Porosity (cm <sup>3</sup> /g)
Alkylammonium montmorillonites (CEC = 85 meq/100 g)					
CH <sub>3</sub> NH <sub>3</sub> <sup>+</sup>	746	21.6	2.2	294	0.065
C <sub>2</sub> H <sub>5</sub> NH <sub>3</sub> <sup>+</sup>	755	29.8	3.4	214	0.073
n-C <sub>3</sub> H <sub>7</sub> NH <sub>3</sub> <sup>+</sup>	765	35.6	3.7	184	0.068
n-C <sub>4</sub> H <sub>9</sub> NH <sub>3</sub> <sup>+</sup>	774	41.4	3.9	155	0.060
n-C <sub>5</sub> H <sub>11</sub> NH <sub>3</sub> <sup>+</sup>	783	47.1	4.0	126	0.050
n-C <sub>6</sub> H <sub>13</sub> NH <sub>3</sub> <sup>+</sup>	792	52.9	4.0	98	0.039
α, ω-alkyldiammonium montmorillonites (CEC = 85 meq/100 g)					
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>2</sub> NH <sub>3</sub> <sup>+</sup>	746	34.8	2.8	278	0.078
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>3</sub> NH <sub>3</sub> <sup>+</sup>	750	40.6	3.5	262	0.092
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>4</sub> NH <sub>3</sub> <sup>+</sup>	755	46.4	4.0	246	0.098
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>5</sub> NH <sub>3</sub> <sup>+</sup>	759	52.2	3.9	231	0.090
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>6</sub> NH <sub>3</sub> <sup>+</sup>	764	58.0	3.8	216	0.082
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>7</sub> NH <sub>3</sub> <sup>+</sup>	769	63.7	3.9	201	0.078
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>8</sub> NH <sub>3</sub> <sup>+</sup>	773	69.5	3.9	187	0.073
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>9</sub> NH <sub>3</sub> <sup>+</sup>	778	75.3	3.9	172	0.067
α, ω-alkyldiammonium hectorites (CEC = 91 meq/100 g)					
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>2</sub> NH <sub>3</sub> <sup>+</sup>	769	34.8	2.8	240	0.067
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>3</sub> NH <sub>3</sub> <sup>+</sup>	774	40.6	3.6	224	0.080
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>4</sub> NH <sub>3</sub> <sup>+</sup>	779	46.4	[3.9]	208	[0.081]
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>5</sub> NH <sub>3</sub> <sup>+</sup>	783	52.2	3.9	192	0.075
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>6</sub> NH <sub>3</sub> <sup>+</sup>	802	75.3	3.9	128	0.050

CEC = cation-exchange capacity.

<sup>1</sup> g.u.c. = gram unit cell.

<sup>2</sup>  $d_1$  = the free distance between adjacent siliceous layers (see Figure 4).

Table 4. Pore volumes in Co(III)(en)<sub>3</sub>-fluorhectorites-90 and -150<sup>1</sup> estimated from monolayer saturation capacities,  $v_m$  (Barrer and Craven, 1987).

Sorbate	Temp. (K)	$v_m$ (cm <sup>3</sup> at stp./g)	Volume at T (cm <sup>3</sup> /mole)	cm <sup>3</sup> (liq) per g of sorbent
Co(III)(en) <sub>3</sub> -FH90				
O <sub>2</sub>	77.3	67. (8)	26.5	0.08 (0)
O <sub>2</sub>	90.2	66. (5)	27.9	0.08 (3)
N <sub>2</sub>	77.3	51. (3)	34.7	0.07 (9)
N <sub>2</sub>	90.2	45. (7)	37.4	0.07 (6)
Ar	77.3	65. (6)	27.4	0.08 (0)
Ar	90.2	63. (7)	29.1	0.08 (3)
CH <sub>4</sub>	90.2	50. (0)	38.7	0.08 (6)
iso-C <sub>8</sub> H <sub>10</sub>	273.2	19. (2)	100.1	0.08 (6)
neo-C <sub>5</sub> H <sub>12</sub>	273.2	23. (7)	117.4	0.12 (4)
CO <sub>2</sub>	273.2	31. (4)	47.4	0.06 (6)
Co(III)(en) <sub>3</sub> -FH150				
O <sub>2</sub>	77.3	51. (7)	26.5	0.06 (1)
O <sub>2</sub>	90.2	49. (3)	27.9	0.06 (1)
CO <sub>2</sub>	273.2	21. (4)	47.4	0.04 (5)

<sup>1</sup> See terminology explained in footnote in Table 1.

#### Intercalation modified by cation shape and size

Examples of molecules intercalated or excluded in MeNH<sub>3</sub>-, Me<sub>2</sub>NH<sub>2</sub>-, Me<sub>3</sub>NH-, Me<sub>4</sub>N-, and Et<sub>4</sub>N-montmorillonite A are given in Table 5 together with values of  $d(001)$  and  $d_1$  for the outgassed sorbents, the external areas,  $A_e$ , and the free interlamellar areas,  $A_i$  (Barrer and MacLeod, 1955; Barrer and Reay, 1957). Whether or not intercalation occurred was often very dependent upon temperature, indicating activated diffusion ( $D = D_0 \exp(-E/RT)$ ). As an example from Table 5, O<sub>2</sub> and N<sub>2</sub> were intercalated in the Et<sub>4</sub>N-montmorillonite A at 78 K, but the uptake of Ar and CH<sub>4</sub> was slight. The approximate van der Waals dimensions of the molecules are: O<sub>2</sub>, 2.8 × 3.9 Å; Ar, 3.8<sub>3</sub> Å; N<sub>2</sub>, 3.0 × 4.1 Å; CH<sub>4</sub>, ~ 4 Å. Another example of fine tuning to molecular dimensions at low temperatures is illustrated in Figure 6 for uptakes of O<sub>2</sub> and N<sub>2</sub> in Co(III)(en)<sub>3</sub>-fluorhectorite-150. At 77.3 K O<sub>2</sub> was copiously sorbed, but on the time scale of the experiment, N<sub>2</sub> was not (Craven, 1976; Barrer, 1978; Barrer and Craven, 1987).

At 323 K Me<sub>4</sub>N- and Et<sub>4</sub>N-montmorillonite intercalated some rather bulky molecules including neopentane (Table 5). In contrast, the MeNH<sub>3</sub>-form at 323 K did not intercalate iso-C<sub>8</sub>H<sub>18</sub>, iso-C<sub>8</sub>H<sub>16</sub>, or cyclohexane, although it freely intercalated n-paraffins, cyclopentane, and aromatics.

As already noted, intercalation was sometimes accompanied by further significant increases in  $d(001)$ . For example, n-paraffins increased  $d(001)$  from 11.6 to 13 Å in MeNH<sub>3</sub>-montmorillonite and benzene increased  $d(001)$  to 15 Å in this form. Benzene also increased  $d(001)$  from 13.5 to 14.6 Å in the Me<sub>4</sub>N-form. The  $d(001)$  values of 15 and 14.6 Å corresponded to benzene molecules stacked on edge between the cations (Barrer and Perry, 1961a, 1961b).




Figure 5. Rates of intercalation at 50°C of n-octane in ed-fluorhectorite-90 (left) and ed-fluorhectorite-150 (right) (ed = ethylenediammonium).  $Q_t$  denotes amount sorbed at time  $t$ , and  $Q_\infty$  is this amount at equilibrium (Barrer and Jones, 1971).

The small interlayer free area,  $A_i$ , of the Et<sub>4</sub>N-montmorillonite and the  $d_1$  of only 4.5(5) Å ( $d(001) = 13.95$  Å) require a flattened conformation of the organic ion, which can be seen with a model (Barrer and MacLeod, 1955). The flattened form covers more of the interlayer area than the other cations. The free areas,  $A_i$ , of Me<sub>4</sub>N- and Et<sub>4</sub>N-montmorillonite are compared for some guest molecules in Table 6. At 323 K the ratio of  $A_i$  for the largest molecules is nearly independent of molecular shape and size.

#### Cation chain length and intercalation

Figure 7 shows isotherms for N<sub>2</sub> at 78 K in a series of alkylammonium and  $\alpha$ -,  $\omega$ -alkyldiammonium forms of montmorillonite and hectorite (Barrer and Millington, 1967). The numbers on the curves are the carbon numbers of the cations. At  $p/p_0 < 0.6$ , the isotherms are all of type 1. The illustration shows that the uptakes in the alkylammonium-montmorillonite samples decreased with chain length much more rapidly than in




Figure 6. Isotherms for O<sub>2</sub> at 77.3 and 90.2 K and N<sub>2</sub> at 77.3 K in Co(III)(en)<sub>3</sub>-fluorhectorite-150, showing the large differences in uptake (Barrer, 1978).

Table 5. Comparison of some alkylammonium montmorillonites.

Cationic form	MeNH <sub>3</sub> <sup>+</sup>	Me <sub>2</sub> NH <sub>2</sub> <sup>+</sup>	Me <sub>3</sub> NH <sup>+</sup>	Me <sub>4</sub> N <sup>+</sup>	Et <sub>4</sub> N <sup>+</sup>
g.u.c. wt.	740	749	759	768	806
d(001) (Å)	12	12.2	13.0	13.5	13.9 (5)
d <sub>1</sub> (Å)	2.6	2.8	3.6	4.1	4.5 (5)
A <sub>e</sub> (m <sup>2</sup> /g)	21.5	21.2	21.0	20.7	19.7
A <sub>i</sub> (m <sup>2</sup> /g)	140	127	105	121	68
Temp. (K)	Some molecules intercalated at the temperature in column 1				
78	N <sub>2</sub>				
90	O <sub>2</sub> , N <sub>2</sub> , Ar	O <sub>2</sub> , N <sub>2</sub> , Ar	O <sub>2</sub> , N <sub>2</sub> , Ar	O <sub>2</sub> , N <sub>2</sub> , Ar	O <sub>2</sub> , N <sub>2</sub>
90	CH <sub>4</sub>	CH <sub>4</sub>	CH <sub>4</sub>	CH <sub>4</sub>	
273	n-C <sub>4</sub> , iso-C <sub>4</sub>	n-C <sub>4</sub> , iso-C <sub>4</sub>	n-C <sub>4</sub> , iso-C <sub>4</sub>	n-C <sub>4</sub> , iso-C <sub>4</sub>	
323	n-C <sub>5</sub> , n-C <sub>6</sub>			n-C <sub>5</sub> , n-C <sub>6</sub>	n-C <sub>5</sub> , n-C <sub>7</sub>
323	cyclo-C <sub>5</sub>			cyclo-C <sub>5</sub>	iso-C <sub>8</sub>
323	benzene			iso-C <sub>5</sub> , iso-C <sub>8</sub>	neo-C <sub>5</sub>
323	toluene			neo-C <sub>5</sub>	benzene
323	o-xylene			benzene	methanol
323	p-xylene			toluene	t-butanol
323				o-, p-xylene	
323				methanol	
323				t-butanol	
Temp. (K)	Molecules showing little intercalation at the temperature in column 1				
78					Ar, CH <sub>4</sub>
323	cyclo-C <sub>6</sub>				
323	iso-C <sub>5</sub> , iso-C <sub>8</sub>				
323	neo-C <sub>5</sub>				

g.u.c. = gram unit cell.

the alkyldiammonium-montmorillonite samples. For example, n-C<sub>3</sub>H<sub>11</sub>NH<sub>3</sub><sup>+</sup> and <sup>+</sup>NH<sub>3</sub>(CH<sub>2</sub>)<sub>4</sub>NH<sub>3</sub><sup>+</sup> have about the same length, but the N<sub>2</sub> uptakes were much larger for the NH<sub>3</sub>(CH<sub>2</sub>)<sub>4</sub>NH<sub>3</sub>-form. One reason for this is that the number of the divalent ions was only half the number of the monovalent ions in each homoionic form. Therefore, more free interlayer area was present with the divalent ions.

#### Intercalation modified by cationic and by lamellar charge

The importance of cationic charge has already been illustrated in Figure 7, if N<sub>2</sub> isotherms in the alkylammonium and alkyldiammonium series of montmorillonites are compared. The importance of layer charge on the siliceous sheets is illustrated by comparing the synthetic fluorhectorite samples listed in Table 1. These fluorhectorite samples, after correcting for impurities, had cation-exchange capacities of 90 and 150 meq/100 g, and were therefore termed FH90 and FH150. They were examined in their non-porous Na-forms and in their microporous MeNH<sub>3</sub><sup>+</sup>, Me<sub>4</sub>N<sup>+</sup>, NH<sub>3</sub>(CH<sub>2</sub>)<sub>2</sub>NH<sub>3</sub><sup>+</sup>, and Co(III)(en)<sub>3</sub>-forms.

In the non-porous Na-forms the external surfaces were small (11 and 8 m<sup>2</sup>/g). Accordingly, isotherms of the microporous forms were little affected by this small external surface except as p/p<sub>0</sub> approached unity and,

as in zeolites, isotherms were of type 1. This is seen in Figure 8 for n-octane at 50°C in each of the ethylenediammonium (ed) forms (Barrer and Jones, 1971). The smaller saturation capacity of the ed-FH150 sample was a consequence of the large layer charge and therefore an increased number of ethylenediammonium ions per unit of interlayer area. Sample FH150 appears to be a vermiculite, rather than a smectite.

Table 7 gives examples, among the guest molecules

Table 6. Comparison of interlayer free areas, A<sub>i</sub>, in Me<sub>4</sub>N- and Et<sub>4</sub>N-montmorillonites.

Guest	Temp. (K)	δ <sup>1</sup> (Å) <sup>2</sup>	A <sub>i</sub> /m <sup>2</sup> /g in:		Ratio of A <sub>i</sub> values
			Me <sub>4</sub> N-form	Et <sub>4</sub> N-form	
O <sub>2</sub>	78	13.6	143	68	2.1 (0)
O <sub>2</sub>	90	14.1	142	77	1.8 (4)
N <sub>2</sub>	78	16.2	149	40 <sup>3</sup>	3.7 (3)
CH <sub>3</sub> OH	323	17.7	131	50	2.6 (2)
C <sub>6</sub> H <sub>6</sub>	323	25 <sup>2</sup>	143	42	3.4 (0)
(CH <sub>3</sub> ) <sub>3</sub> COH	323	32.4	129	33. (3)	3.8 (7)
n-C <sub>5</sub> H <sub>12</sub>	323	47.9	130	34. (0)	3.8 (2)
n-C <sub>7</sub> H <sub>16</sub>	323	64	132	32. (4)	4.0 (7)
iso-C <sub>8</sub> H <sub>18</sub>	323	67	109	28. (7)	3.8 (0)

<sup>1</sup> δ denotes the molecular co-area.

<sup>2</sup> Cross-sectional area for C<sub>6</sub>H<sub>6</sub> on edge.

<sup>3</sup> This low value at 78 K may be due to non-equilibrium.




Figure 7. Sorption of  $N_2$  at 78 K by (a) alkylammonium montmorillonites, (b) alkyldiammonium montmorillonites, and (c) alkyldiammonium hectorites. The number on each curve gives the carbon number of the cation. Isotherms in the parent Na-form are also shown (Barrer and Millington, 1967).

actually studied, of intercalation in and exclusion from the exchange forms of samples FH90 and FH150. Especially in the  $Co(III)(en)_3$ -FH150 sample, intercalation was, as already seen in Figure 6 for  $O_2$  and  $N_2$ , very sensitive to molecular dimensions and temperature. Figure 9 further illustrates this sensitivity in the dramatic differences in rates of uptake in the  $Co(III)(en)_3$ -FH150 sample for  $H_2$ ,  $D_2$ , Ne, and  $O_2$  (very fast at 77.3 and 90.2 K) and  $N_2$ , Ar, and  $CH_4$  (very slow at 77.3 and 90.2 K).

The virtual exclusion of  $O_2$ ,  $N_2$ , and Ar from the micropores of the  $MeNH_3$ -forms of samples FH90 and FH150 at 78 K is noteworthy, because these gases were all intercalated at similar temperatures by  $MeNH_3$ -montmorillonite. The cation-exchange capacities of sample FH90 and the montmorillonite were nearly the same (90 and 91 meq/100 g (Table 1)). Therefore, the interlamellar free distance between adjacent cations ( $d_3$  of Figure 4) was almost the same, and so was the vertical free distance,  $d_1$ , between sheets ( $\sim 2.2$  Å).

This difference in behavior represents another significant variable, which was considered to have arisen from differences in the size and perfection of the crystallites. Thus, sample FH90 and the Na-rich montmorillonite used had respectively about 85 and 26 lamellae per average crystal, and the crystals of sample FH90 were much larger. For penetration of  $O_2$ ,  $N_2$ , or Ar into the  $MeNH_3$ -forms expansion in  $d_1$  was needed, involving nucleation of the expanded phase at crystal edges. At 78 K this nucleation, as the prerequisite for penetration, occurred only in the  $MeNH_3$ -montmorillonite, in which the smaller flake size and number of lamellae per crystal were more favorable for nucleation.

Differences between a given cationic form of sample FH90 and the corresponding form of sample FH150

could not have arisen from  $d_1$ , because  $d_1$  was the same. The differences must have arisen primarily from  $d_3$ , estimates of which are given below (Barrer and Jones, 1971):

Cation	$d_3$ , FH90(Å)	$d_3$ , FH150(Å)	$d_1$ (Å)
$Me_4N^+$	$\sim 2.7$	$\sim 0.8$	4.0
$[NH_3(CH_2)_2NH_3]^{2+}$	$\sim 4.9$ to $7.5^*$	$\sim 3.8$ to $5.3^*$	2.8
$Co(en)_3^{3+}$	6.7	3.4	4.2

where \* means according to the mutual pair orientation. As was observed experimentally, on the basis of the above estimates, the failure of  $Me_4N$ -fluorhectorite-150 to intercalate  $N_2$  at 78 K was to be expected.




Figure 8. Sorption isotherms of n-octane at 323 K, in (a) ed-fluorhectorite-90 and (b) ed-fluorhectorite-150. ●, sorption; ○, desorption; ed = ethylenediammonium (Barrer and Jones, 1971).




Figure 9. Sorption rates for H<sub>2</sub>, D<sub>2</sub>, O<sub>2</sub>, N<sub>2</sub>, Ne, Ar, Kr, and CH<sub>4</sub> in Co(III)(en)<sub>3</sub>-fluorhectorite-150. At 77.3 and 90.2 K the group He, D<sub>2</sub>, O<sub>2</sub>, and Ne, which are all intercalated very rapidly, are strongly differentiated from the group N<sub>2</sub>, Ar, and CH<sub>4</sub>, which are intercalated very slowly, if at all (Barrer, 1978).

#### PARTIAL EXCHANGE AND SORPTION CAPACITY

A series of partially exchanged (Na, MeNH<sub>3</sub>)- and (Na, Me<sub>4</sub>N)-montmorillonite samples was investigated to see whether partial exchange could enhance the sorption capacity. An enhancement was to be expected if Na<sup>+</sup> and an organic cation were randomly mixed in each interlayer region. The free interlamellar area, however, was found to be almost exactly proportional to the equivalent cation fraction of the interlayer organic ion. The only explanation is that the partially

exchanged crystals contained a mixture of interstratified cation layers, some containing only organic cations and the rest only Na<sup>+</sup> (Barrer and Brummer, 1963).

Incomplete exchange is thus an important variable if sorption capacities are compared, either among different cationic forms or for the same cationic form prepared in different laboratories.

#### THERMAL STABILITY

The thermal stability of smectite molecular sieves is determined by that of the interlamellar cations, if these

Table 7. Examples of intercalation and exclusion in fluorhectorite-90 and -150 (FH90 and FH150).<sup>1</sup>

Cationic form	d(001) (Å)	d <sub>1</sub> (Å)	Temp. (K)	Intercalation in FH90		Intercalation in FH150				
				Yes	No	Yes	No			
MeNH <sub>3</sub> <sup>+</sup>	11.6	2.2	78		O <sub>2</sub> , N <sub>2</sub> , Ar		O <sub>2</sub> , N <sub>2</sub> , Ar			
Me <sub>4</sub> N <sup>+</sup>	13.4	4.0	78	O <sub>2</sub> , N <sub>2</sub> , Ar			N <sub>2</sub>			
+NH <sub>3</sub> (CH <sub>2</sub> ) <sub>2</sub> NH <sub>3</sub> <sup>+</sup>	12.2	2.8	78	O <sub>2</sub> , N <sub>2</sub> , Ar		O <sub>2</sub> , N <sub>2</sub> , Ar				
			273	n-C <sub>4</sub> , iso-C <sub>4</sub>		n-C <sub>4</sub> , iso-C <sub>4</sub>				
			323	n-C <sub>8</sub>		n-C <sub>8</sub>				
			323	2,3-di-Me-C <sub>4</sub>	2,3-di-Me-C <sub>4</sub>	2,3-di-Me-C <sub>4</sub>	2,2-di-Me-C <sub>4</sub>			
			323	cyclo-C <sub>5</sub>	neo-C <sub>5</sub>	cyclo-C <sub>5</sub>	neo-C <sub>5</sub>			
			323	cyclo-C <sub>6</sub>	2,2,4-tri-Me-C <sub>5</sub>	benzene	cyclo-C <sub>6</sub>			
			323	benzene			2,2,4-tri-Me-C <sub>5</sub>			
			323	toluene						
			323	m-xylene			toluene, m-xylene			
			323	mesitylene			mesitylene			
			Co(en) <sub>3</sub> <sup>3+</sup>	13.6	4.2	77.3	H <sub>2</sub> , D <sub>2</sub> , Ne, Ar		H <sub>2</sub> , D <sub>2</sub> , Ne, O <sub>2</sub>	N <sub>2</sub> , Ar
						77.3	O <sub>2</sub> , N <sub>2</sub>			
90.2	H <sub>2</sub> , D <sub>2</sub> , Ne, Ar					O <sub>2</sub>	CH <sub>4</sub> , Ar			
90.2	O <sub>2</sub> , N <sub>2</sub> , CH <sub>4</sub>									
194.7	Kr, CH <sub>4</sub>					Kr, CH <sub>4</sub>				
273.2	Kr, CO <sub>2</sub>									
273.2	iso-C <sub>4</sub>									
273.2	neo-C <sub>5</sub>									

<sup>1</sup> See explanation of terminology in footnote in Table 1.

are alkylammonium ions or Co(en)<sub>3</sub><sup>3+</sup>. For the latter ion, a thermogravimetric analysis in air indicated negligible decomposition at <100°C up to complete decomposition at 250°C (Barrer and Jones, 1971). Several alkylammonium forms of montmorillonite A were also examined by outgassing each of them at a series of increasing temperatures and comparing the BET monolayer equivalent areas with that of the same form outgassed at 50°C. Figure 10 shows that all forms were stable to outgassing to ~150°C, and that the MeNH<sub>3</sub>-form was least stable and the Me<sub>4</sub>N-form most stable (Barrer and Reay, 1957).

### SEPARATION

Factors which make permanently expanded clay minerals attractive for separations include the following: (1) Clear selectivity sequences are common for molecules of different structural types, such as aromatics and n-, iso-, neo-, and cycloparaffins, and are enhanced for certain of these by molecule sieving. (2) High rates of sorption are found near room temperature (cf. Figure 5), and the intercalated molecules can be rather easily desorbed. (3) Intercalation capacities are satisfactory. Thus, in NH<sub>3</sub>(CH<sub>2</sub>)<sub>2</sub>NH<sub>3</sub>-fluorhectorite-90 and -150 (respectively, termed ed-FH90 and ed-FH150, where ed = NH<sub>3</sub>(CH<sub>2</sub>)<sub>2</sub>NH<sub>3</sub>) observed uptakes of typical hydrocarbons in wt. % were (Barrer and Jones, 1971):

Sorbate	wt. % in:	
	ed-FH90	ed-FH150
n-hexane	—	6.7
n-octane	6.9	6.4

2,3-dimethylbutane	5.1	4.5
cyclopentane	7.2	7.6
cyclohexane	5.9	not intercalated
benzene	12.9	8.1
toluene	9.6	not intercalated
m-xylene	5.6	not intercalated
mesitylene	5.4	not intercalated

Isotherms were determined at 349.8 or 353 K for the following binary mixtures with feed mixtures of constant composition for each mixture isotherm, but changing these compositions over a given series of isotherms (Barrer and Hampton, 1957; Barrer and Perry, 1961a, 1961b):

Mixture	Cationic form of montmorillonite		
	Et <sub>4</sub> N-	Me <sub>4</sub> N-	MeNH <sub>3</sub> -
C <sub>6</sub> H <sub>6</sub> + n-C <sub>7</sub> H <sub>16</sub>	+	+	+
n-C <sub>7</sub> H <sub>16</sub> + cyclo-C <sub>6</sub> H <sub>12</sub>	—	+	+
n-C <sub>6</sub> H <sub>4</sub> + iso-C <sub>8</sub> H <sub>18</sub>	—	+	+
cyclo-C <sub>6</sub> H <sub>12</sub> + iso-C <sub>8</sub> H <sub>18</sub>	—	+	+
C <sub>6</sub> H <sub>6</sub> + CH <sub>3</sub> OH	—	+	+
C <sub>6</sub> H <sub>6</sub> + cyclo-C <sub>6</sub> H <sub>12</sub>	—	—	+
CH <sub>3</sub> OH + CCl <sub>4</sub>	—	+	—

where + or — denote systems for which mixture isotherms were or were not determined. Figure 11 compares the mixture isotherms for the pairs benzene + methanol and benzene + n-heptane in the Me<sub>4</sub>N- and MeNH<sub>3</sub>-montmorillonite samples. The illustration shows the selectivity to be the opposite in the two sorbents for benzene + methanol and that a cross-over in selectivity exists in the MeNH<sub>3</sub>-form for benzene +






Figure 10. The BET monolayer equivalent areas, measured by N<sub>2</sub> sorption as functions of outgassing temperature for MeNH<sub>3</sub>-, Me<sub>2</sub>NH<sub>2</sub>-, Me<sub>3</sub>NH-, and Me<sub>4</sub>N-montmorillonite samples. The areas are expressed as percentage of the area obtained on outgassing at 50°C (Barrer and Reay, 1957).

n-heptane. These selectivity data illustrate the strong influence of the exchange ion on separation factors.

Separation factors are defined for component A in a mixture of A + B as

$$\eta_A = n_A^S n_B^G / n_B^S n_A^G = n_A^S p_B / n_B^S p_A, \quad (1)$$

where n denotes mole and p is partial pressure. The superscripts "S" and "G" denote sorbed and gaseous, respectively, and the subscripts "A" and "B" denote the two components. If the sorbent provides two distinct sorbing regions (external and interlamellar), the separation factors for each are  $\eta_A^a$  and  $\eta_A^i$ , respectively, where,

$$\left. \begin{aligned} \eta_A^a &= n_A^a p_B / n_B^a p_A \\ \eta_A^i &= n_A^i p_B / n_B^i p_A \end{aligned} \right\} \quad (2)$$

and where superscripts "a" and "i" denote adsorbed and interlamellar. Also

$$\left. \begin{aligned} n_A^S &= n_A^a + n_A^i \\ n_B^S &= n_B^a + n_B^i \end{aligned} \right\} \quad (3)$$

If Eq. (3) is substituted in Eq. (1) and the result rearranged, using Eq. (2), one obtains the general result (Barrer and Perry, 1961a):

$$n_B^S \eta_A = n_B^i \eta_A^i + n_B^a \eta_A^a, \quad (4)$$

for the influence of  $\eta_A^i$  and  $\eta_A^a$  upon the overall separation factor,  $\eta_A$ . For the special but important case in which component A is intercalated but B is not,

$$\eta_A = \eta_A^a (1 + n_A^i / n_A^a). \quad (5)$$

Eq. (5) applies, for example, if one component is a




Figure 11. Comparison of isotherms at 76.8°C for binary mixtures on Me<sub>4</sub>N- and MeNH<sub>3</sub>-montmorillonites. The numbers allow corresponding points on each isotherm to be identified. The mole fractions of benzene in the feeds were (a) 0.37, (b) 0.40, (c) 0.60, and (d) 0.59 (Barrer and Hampton, 1957).

n-paraffin and the other is iso-octane or cyclohexane and the sorbent is MeNH<sub>3</sub>-montmorillonite-A of Table 1.

Figure 12 shows for Me<sub>4</sub>N-montmorillonite the separation factors for benzene + n-heptane (where both




Figure 12. Separation factors as functions of total equilibrium pressure and of temperature for benzene in a benzene + n-heptane mixture. The sorbent was Me<sub>4</sub>N-montmorillonite, and the feed mixture always contained 0.67 mole fraction of benzene. □, 80°C; ○, 85°C; ×, 90°C; and △, 95°C (Barrer and Perry, 1961b).

Table 8. Composition changes of equilibrium liquid effected with Me<sub>4</sub>N-montmorillonite (Barrer and Hampton, 1957).

Wt. of sorbent (g)	Mixture A + B	mole fraction A	Volume of liquid (cm <sup>3</sup> )	Volume recovered (cm <sup>3</sup> )	Composition of liquid recovered
7.5	C <sub>6</sub> H <sub>6</sub> + iso-C <sub>8</sub> H <sub>18</sub>	0.5	1.5	0.2	~100% iso-C <sub>8</sub> H <sub>18</sub>
	C <sub>6</sub> H <sub>6</sub> + iso-C <sub>8</sub> H <sub>18</sub>	0.5	2.0	0.3	96% iso-C <sub>8</sub> H <sub>18</sub>
6.5	cyclo-C <sub>6</sub> H <sub>12</sub>	0.7	2.0	0.6	97% cyclo-C <sub>6</sub> H <sub>12</sub>
	+ C <sub>6</sub> H <sub>6</sub> (m.f. 0.1)				
	+ thiophene (m.f. 0.1)				
	+ toluene (m.f. 0.1)				
8.5	CH <sub>3</sub> OH + CCl <sub>4</sub>	0.4	1.5	0.25	99% CCl <sub>4</sub>
7.5	C <sub>6</sub> H <sub>6</sub> + n-C <sub>7</sub> H <sub>16</sub>	0.6	1.7	0.2	98% n-C <sub>7</sub> H <sub>16</sub>
7	n-C <sub>7</sub> H <sub>16</sub> + iso-C <sub>8</sub> H <sub>18</sub>	0.67	1.5	0.2	75–80% iso-C <sub>8</sub> H <sub>18</sub>
6	C <sub>6</sub> H <sub>6</sub> + cyclo-C <sub>6</sub> H <sub>12</sub>	0.25	4.5	1.0	92% cyclo-C <sub>6</sub> H <sub>12</sub>

are intercalated) as a function of the total pressure and temperature.  $\eta_{C_6H_6}$  increases with pressure and decreases with rising temperature (Barrer and Perry, 1961b).

In a second approach to separations, liquid mixtures were equilibrated with the sorbent, some of the non-sorbed liquid was centrifuged off, and its composition was compared with that of the initial mixture. The more weakly sorbed component was highly enriched in the liquid recovered, as the results in Table 8 show.

In a third approach, chromatography was used. A volume of liquid of known composition was injected into a stream of dry N<sub>2</sub> passing through a column of sorbent. At 77°C, using the Me<sub>4</sub>N-montmorillonite, separations were achieved for the following pairs (Barrer and Hampton, 1957):

benzene/cyclohexane	cyclo-hexane/cyclo-hexanol
toluene/cyclohexane	n-heptane/methanol
benzene/n-heptane	n-hexane/cyclo-hexane
benzene/carbon tetrachloride	n-heptane/iso-octane
benzene/toluene	n-heptane/cyclo-hexane
methanol/carbon tetrachloride	thiophene/benzene

The sorbent is notable for the selectivity shown for the aromatics and for thiophene and for its preference for n-paraffins compared with cyclo- and branched-chain paraffins.

With MeNH<sub>3</sub>-montmorillonite separations were effected for the mixtures: benzene/cyclo-hexane, benzene/iso-octane, methanol/toluene, benzene/toluene, n-heptane/methanol. In this sorbent the selectivity for aromatics over n-paraffins was reduced and at low loadings may have been reversed. Aromatics were preferred over cyclo- and branched chain paraffins.

#### CONCLUDING REMARKS

This summary of part of our work on microporous clay minerals illustrates their potential as sorbents. In recent years, with a view to obtaining larger pores and

increased thermal and hydrothermal stability, others have used various oligomeric inorganic oxycations of Al, (Al, Si), Si, Ti, Zr, Cr, and Fe as props to separate the sheets (cf. Vaughan, 1988). The products usually have greater interlayer free distances than organoclays and are providing a new chapter in the story of porous layer silicates. They may prove to be sorbents and catalysts significant in the wider saga of porous crystals, comprising zeolites, porosils, AlPOs, microporous organoclays, and certain Werner complexes and clathrates. These so-called pillared clays (PILCs) provide meso- as well as micropores, and require more detailed characterization.

#### REFERENCES

- Barrer, R. M. (1978) *Zeolites and Clay Minerals as Sorbents and Molecular Sieves*: Academic Press, New York, pp. 474, 476.
- Barrer, R. M. (1984) Sorption and molecular sieve properties of clays and their importance as catalysts: *Phil. Trans. Roy. Soc. London A* **311**, 333–352.
- Barrer, R. M. (1986) Expanded clay minerals: A major class of molecular sieves: *J. Inclusion Phenomena* **4**, 109–119.
- Barrer, R. M. and Brummer, K. (1963) Relations between partial ion exchange and interlamellar sorption in alkylammonium montmorillonites: *Trans. Faraday Soc.* **59**, 959–968.
- Barrer, R. M. and Craven, R. J. B. (1987) Smectite molecular sieves. Part II. Expanded fluorhectorite sorbents: *J. Chem. Soc. Faraday Trans. I* **83**, 779–787.
- Barrer, R. M. and Hampton, M. G. (1957) Gas chromatography and mixture isotherms in alkylammonium bentonites: *Trans. Faraday Soc.* **53**, 1462–1475.
- Barrer, R. M. and Jones, D. L. (1970) Chemistry of soil minerals. Part VIII. Synthesis and properties of fluorhectorites: *J. Chem. Soc. A*, 1531–1537.
- Barrer, R. M. and Jones, D. L. (1971) Chemistry of soil minerals. Part X. Shape-selective sorbents derived from fluorhectorites: *J. Chem. Soc. A*, 2594–2603.
- Barrer, R. M. and Kelsey, K. E. (1961a) Thermodynamics of interlamellar complexes. Part I. Hydrocarbons in methylammonium montmorillonites: *Trans. Faraday Soc.* **57**, 452–462.
- Barrer, R. M. and Kelsey, K. M. (1961b) Thermodynamics of interlamellar complexes. Part II. Hydrocarbons in dimethyldioctadecylammonium bentonite: *Trans. Faraday Soc.* **57**, 625–640.
- Barrer, R. M. and Mackenzie, N. (1954) Sorption by attapulgite

- pulgite. Part I. Availability of intracrystalline channels: *J. Phys. Chem.* **58**, 560–568.
- Barrer, R. M., Mackenzie, N., and (in part) MacLeod, D. M. (1954) Sorption by attapulgite. Part II. Selectivity shown by attapulgite, sepiolite and montmorillonite for n-paraffins: *J. Phys. Chem.* **58**, 568–572.
- Barrer, R. M. and MacLeod, D. M. (1954) Intercalation and sorption by montmorillonite: *Trans. Faraday Soc.* **50**, 980–989.
- Barrer, R. M. and MacLeod, D. M. (1955) Activation of montmorillonite by ion exchange and sorption complexes of tetra-alkylammonium montmorillonites: *Trans. Faraday Soc.* **51**, 1290–1300.
- Barrer, R. M. and Millington, A. D. (1967) Sorption and intracrystalline porosity in organoclays: *J. Coll. Interface Sci.* **25**, 359–372.
- Barrer, R. M. and Perry, G. S. (1961a) Sorption of mixtures and selectivity in alkylammonium montmorillonites. Part I. Monomethylammonium bentonite: *J. Chem. Soc.*, 842–849.
- Barrer, R. M. and Perry, G. S. (1961b) Sorption of mixtures and selectivity in alkylammonium montmorillonites. Part II. Tetramethylammonium montmorillonite: *J. Chem. Soc.*, 850–858.
- Barrer, R. M. and Reay, J. S. S. (1957) Sorption and intercalation by methylammonium montmorillonites: *Trans. Faraday Soc.* **53**, 1253–1261.
- Brunauer, S. (1944) *The Physical Adsorption of Gases and Vapours*: Oxford Univ. Press, Oxford, United Kingdom, p. 150.
- Craven, R. J. B. (1976) Sorption and separation by ion-exchanged synthetic fluorhectorites: Ph.D. thesis, London University, pp. 164, 231.
- Vaughan, D. E. W. (1988) Recent developments in pillared interlayered clays: Preprint from *Perspectives in Molecular Sieve Science*, W. H. Flank and T. E. Whyte, Jr., eds., Amer. Chem. Soc. Symposium, Toronto, 1988.

(Received 20 September 1988; accepted 16 February 1989; Ms. 1832)