NOTE

ADSORPTION OF PHOSPHATE ON IMOGOLITE

(Received 3 *December 1973)*

Imogolite is a hydrous aluminum silicate which has been found in many volcanic ash soils. Electron microscopy has shown that the mineral consists of bundles of tubes with a length of about 1 μ m. The bundles have a diameter of 10·0-30·0 nm with individual tubes having external and internal diameters of 2·0 and 1·0 nm respectively.

The structure of the external surface of the tubes is similar to the gibbsite (001) face. The internal surface has silica tetrahedra above vacant octahedral sites so that SiOH groups are protruding from the surface (Cradwick *et al.,* 1972).

Since volcanic ash soils are capable of fixing large amounts of phosphate, particularly *if* aluminum rich allophane is present, the adsorption of phosphate on imogolite has been studied as a model system (Cloos *et al., 1968).*

Imogolite was separated from macroscopic gel film collected from the Kitakami pumice bed. Extractable oxides were removed by treating 100 mg of imogolite with 0·5 M NaHCO₃ and 0.5 g Na₂S₂O₄ at 80°C (15 min), centrifuging and washing with 50 ml 0^{·05} M HCl (15 min) followed by further washes with water. After removal of *organic* matter with 6% H₂O₂ the imogolite was washed several times with distilled water, centrifuged and freeze dried.

Ten mg of imogolite were placed in a polythene centrifuge tube, 5 ml 10^{-2} M KCl, 5 ml of a known KH_2PO_4 solution (from $1·3$ to 65 μ moles) added, the pH adjusted by the addition of either dilute HCl or NaOH, and allowed to stand at room temperature (27°C) for 2 days. Longer reaction times did not give detectable changes in the amount of adsorption. Similar but less reproducible results were obtained when tubes were shaken dunng the reaction period. The equilibrium pH was then measured, the suspension centrifuged, and a suitable aliquot (1 or 2 ml) taken for determination

Fig. 1. Phosphate adsorption, μ mole/g imogolite, in 5 x 10- 3 M KCI at **pH** 4·0.

of the equilibrium phosphate concentration by the method of Boltz and Mellon (1947).

The adsorption isotherm of phosphate on imogolite at pH 4⁰ is given in Fig. 1. The plateau for adsorption at pH 4·0 occurs at 280 pmole phosphate per g imogolite. The *iso*therm is similar to those of M *uljadi* er *al.* (1966) for the adsorption of phosphate on gibbsite. Maximum adsorption is observed at low pH and adsorption falls from 280 μ mole at pH 4 to 190 μ mole phosphate per g imogolite at pH 8.

The experimental data could be recalculated very satisfactorily by an equation of the same form as that used by Muljadi, Posner and Quirk (1966),

$$
A = A_1 + \frac{A_2 K[\mathbf{P}]}{1 + K[\mathbf{P}]}
$$

Here *A*, the amount adsorbed at pH 4, is recalculated from A_1 , a high affinity region amounting to 60 μ mole/g, and a Langmuir type term *which* describes a lower affinity region 60-310 μ mole/g *(i.e.* $A_2 = 250$ μ mole/g). [P] is the phosphate concentration. The value of the Langmuir constant, $K = 0.22$ mmolar⁻¹, is somewhat smaller than the *K* values for gibbsite $(K = 1.1 \text{ mmolar}^{-1}$ at pH 3; 0.78 at pH 5) (Muljadi *et al.,* 1966). However, the physical significance of the comparison is uncertain, because the value of *K* for imogolite is sensitive to the choice of values for other parameters and the introduction of additional parameters. Within the concentration range studied here we did not observe adsorption beha vior corresponding to Region **III** postulated by Muljadi *et al. (1966).*

The imogolite has four different types of surfaces. The following estimates of surface area were made by assuming the length of the fibers to be 1 μ m, the diameter of the bundle to be 20 nm, the internal and external diameter of a fiber to be 1·0 and 2·0 nm respectively and the density to be 2·6 g cm⁻³. This gives: (1) ends of tubes $1 \text{ m}^2 \text{g}^{-1}$; (2) outside surface of bundles $100 \text{ m}^2 \text{g}^{-1}$; (3) outside surface of tubes within bundles 900 m²g⁻¹; (4) inside surface of tubes 500 m^2g^{-1} .

By analogy *with* gibbsite the most likely site for adsorption is on the ends of the tubes where AI is coordinated to both OH⁻ and H₂O (Muljadi *et al.,* 1966). If one assumes one phosphate ion covers about 30×10^{-20} m² of surface (Vissers, 1968) then the total surface covered by 280 μ mole phosphate is 50 m^2g^{-1} . Therefore the main part of phosphate adsorption must be at other sites.

The outside surface of bundles of tubes with a surface area of 100 m^2g^{-1} has a structure similar to the gibbsite (001) face except that it will be distorted due to the curvature of the surface. Muljadi er *al.* (1966) thought that the gibbsite (001) face could not absorb phosphate but Parfitt *er al.* (personal communication) found that organic acids were adsorbed on this gibbsite surface. Since Muljadi *et al. (1966)* found that phosphate was adsorbed in large amounts on gibbsite, and in excess of the available edge sites, it seems possible that adsorption of phosphate can also take place on the (001) face.

If the phosphate ion is adsorbed on this surface then half the surface will be covered and one ion will occur on 60 \times 10^{-20} m² of surface or 1.2 unit cells where the area of the unit cell is approximately 50×10^{-20} m² on the outside surface using gibbsite *a*- and *b*-dimensions for imogolite $2\pi/n$ and c-directions (Cradwick *et al.. 1972).*

Imogolite which had been heated to 250° C prior to reaction with phosphate adsorbed more (400 μ mole phosphate/g at pH 40) than untreated imogolite. Heating to 250° C removed water from between the tubes causing the structure to partly collapse. This surface is then less available for adsorption (Wada and Hermi, 1972). Since there was an increase in phosphate adsorption after heating and not a decrease it is not likely that phosphate adsorbs between the tubes. In fact the increased adsorption suggests that more external AI-OH sites become available due to distortion of the fibers.

It is unlikely that phosphate adsorbs inside the tubes since this surface has silanol groups and is silica rich. Silica rich allophanes probably have a similar structure and they are less likely to adsorb phosphate (Saunders, 1965; Cloos *et aI., 1968).*

The adsorption of phosphate by imogolite probably results in coordination of phosphate oxygen atoms by Al^{3+} ions. This mechanism, a ligand exchange reaction, in which phosphate displaces OH^- or H_2O from coordination shells of Al^{3+} or Fe^{3+} has been proposed for some oxide and hydroxide minerals and layer lattice silicates containing iron or aluminum in edge sites (Hingston *et al.,* 1972; Atkinson *et al.,* 1972).

Acknowledgement-The authors thank Dr K. Wada for the generous donation of the imogolite sample.

Atkinson R. J., Posner, A. M. and Quirk, J. P. (1972) Kinetics of isotopic exchange of phosphate at the α -FeOOHaqueous solution interface: *J. [norg. Nucl. Chem. 34,* 2201-2211.

REFERENCES

- Boltz, D. F. and Mellon, M. G. (1947) Determination of phosphorus, germanium, silicon and arsenic by the heteropoly blue method: Anal. Chem. **19,** 873-877.
- Cradwick, P. D. G., Farmer, V. C, Russell, 1. D., Masson, C. R., Wada, K. and Yoshinaga, N. (1972) Imogolite, a hydrated aluminium silicate of tubular structure: *Nature Phys. Sci.* 240,187-189.
- Cloos, P., Herbillon, A. and Echeverria, 1. (1968) Allophanelike synthetic silico-aluminas. Phosphate adsorption and availability: *Trans. 9th lilt. Congress Soil Sri.,* Vo!. 11, pp. 733-743. Adelaide.
- Hingston, F. J., Posner, A. M. and Quirk, 1. P. (1972) Anion adsorption by goethite and gibbsite—I. The role of the proton in determining adsorption envelopes: *J. Soil Sei.* 23, 177-192.
- Muljadi, D., Posner, A. M. and Quirk, 1. P. (1966) The mechanism of phosphate adsorption by kaolinite, gibbsite and pseudoboehmite-I. The isotherms and the effect of pH on adsorption: *J. Soil Sci.* 17, 212-247.
- Parfitt, R. L. and Farmer, V. C. Personal communication.
- Saunders, W. M. H. (1965) Phosphate retention by New Zealand soils and its relationship to free sesquioxides, organic matter and other soil properties: *N.Z. J. Agrie. Res.* 8,30-57.
- Vissers, D. R. (1968) The sorption of ortho-phosphate on crystalline metal oxides: *J. Phys. Chem.* **72**, 32–36.
- Wada, K. and Henmi, T. (1972) Characterization of micropores of imogolite by measuring retention of quaternary ammonium chlorides and water: *Clay Sci.* 4, 127-136.